In the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1   1.   (Canceled).

1   2.   (Canceled).

1   3.   (Canceled).

1   4.   (Canceled).

1   5.   (Canceled).

1   6.   (Canceled).

1   7.   (Canceled).

1   8.   (Canceled).

1   9.   (Canceled).

1   10.   (Canceled).

1   11.   (Canceled).

1   12.   (Currently Amended) The method of claim 11 20, further comprising the
2   step of embedding at least one insert of a material harder than bone in
3   the plastic material.

1   13.   (Previously Presented) The method of claim 12, wherein the at least one

2   insert is fully embedded in the plastic material.

1   14.   (Canceled).

1   15.   (Currently Amended) The ancillary as recited in claim ~~14~~ 21, wherein said

2   ancillary also comprises at least one insert of a material which is harder

3   than bone, said at least one insert being at least partly embedded in said

4   plastic material.

1   16.   (Previously Presented) The ancillary as defined in claim 15, wherein said

2   at least one insert is fully embedded in said plastic material.

1   17.   (Previously Presented) The ancillary as defined in claim 15, wherein said

2   at least one insert is a metal.

1   18.   (Previously Presented) The ancillary as defined in claim 16, wherein said

2   at least one insert is a metal.

1   19.   (Previously Presented) The ancillary as defined in claim 14, wherein said

2   ancillary comprises a part of a shape memory material harder than said

3   plastic material.

1   20.   (New) A method for manufacturing an ancillary used to remove bone,

2   comprising the steps of:

3   providing a body having the shape of an ancillary and comprising a

4   part in a plastic material which is to come into contact with bone to be

5   removed when said ancillary is used to remove the bone; and

6   exposing said plastic material to β or γ rays, so that after this

7   exposition, said plastic material is hard enough to remove bone when

8   said ancillary is used and when said ancillary is put into an autoclave at at

9   least 137°C, said ancillary deteriorates itself and cannot be used

10   anymore.

1   21.   (New) An ancillary for removing bone, comprising a part in a plastic

2   material of which is to come into contact with bone to be removed when

3   said ancillary is used, said plastic material being hard enough to remove

4   bone when said ancillary is used, and when said ancillary is put into an

5   autoclave at at least 137°C, said ancillary deteriorates itself and cannot

6   be used anymore.

Docket No. CAC.P0046